



ADVANTAGES OF FIBERMESH 650 MACRO FIBERS:

- Non-magnetic
- Rustproof
- Alkali proof
- Requires no minimum amount of concrete cover
- Always positioned in compliance with codes
- Safe and easier to use than traditional reinforcement
- Reduces construction time

FIBERMESH 650 MACRO-SYNTHETIC FIBER

Fibermesh 650 is an engineered graded macro-synthetic fiber featuring e3 patented* technology manufactured to an optimum gradation and highly oriented to allow greater surface area contact within the concrete resulting in increased inter-facial bonding and flexural toughness. Fibermesh 650 is made with 100% virgin olefin materials. Specifically engineered and manufactured in our ISO 9001:2008 certified facility for use as concrete reinforcement.

*Covered by US Patent # 5628822, 5456752

FEATURES & BENEFITS

- Graded macro-synthetic fiber for concrete reinforcement
- Alternative to traditional steel wire fabric and rebar
- Provides impact, abrasion and shatter resistance
- Greater surface area provides increased flexural toughness (residual strength)
- Improved ductility
- Provides improved durability
- Control of drying shrinkage and temperature cracking
- Pumpable reinforcement

PRIMARY APPLICATIONS

- Slabs-on-ground
- Sidewalks /Driveways
- Parking areas
- Overlays & toppings
- Exterior pavements
- Non-magnetic applications
- Shotcrete
- Composite metal decks

COMPLIANCE

- Complies with European Standard EN 14889-2:2006 Fibres for Concrete Part 2: Class II and carries CE marking
- UL Classified: For use as an alternate or in addition to the welded wire fabric used in Floor-Ceiling D700, D800, D900 Series Designs. Fibers may also be used in Floor-Ceiling Design Nos. G229, G243, G256, G514
- Complies with ASTM C 1116/C 1116M, Type III fiber reinforced concrete.
- ISO 9001:2008 Quality Assured Facility

CHEMICAL AND PHYSICAL PROPERTIES

Absorption	<i>Nil</i>	Ignition Point	<i>759.2°F (404°C)</i>
Acid & Salt Resistance	<i>High</i>	Melt Point	<i>320°F (160°C)</i>
Alkali Resistance	<i>Alkali Proof</i>	Specific Gravity	<i>0.91</i>
Electrical Conductivity	<i>Low</i>	Thermal Conductivity	<i>Low</i>
Fiber Length*	<i>Graded</i>	Young's Modulus	<i>725-1015 ksi (5-7 GPa)</i>

*Also available in single cut lengths

WE ARE THE CONCRETE FIBER EXPERTS

WWW.FIBERMESH.COM



FIBERMESH®
BY PROPEX

PRODUCT DATA • FIBERMESH® 650-e3®

PRODUCT USE

MIXING: Fibermesh 650 macro reinforcing is a mechanical, not chemical, process. Due to fiber efficiency, minor mix design modifications may be required depending on the application. Consult your Fibermesh representative for recommendations. Fibermesh 650 fiber is added to the mixer during or after batching the other concrete materials. After the addition of the fibers, the concrete should be mixed for a sufficient time (batch plant: minimum 5 minutes or 70 revolutions) at full mixing speed to ensure uniform distribution of the fibers throughout the concrete mix. Mixing times may vary, please contact Fibermesh representative.

PLACING: Fibermesh 650 macro-reinforced concrete can be pumped, sprayed or placed using conventional equipment.

FINISHING: Fibermesh 650 macro-reinforced concrete can be finished by normal finishing techniques.

APPLICATION RATE: The standard application rate for Fibermesh 650 fibers is a minimum 3 lbs/yd³, (2 kg/m³). For specific performance and dosage recommendations see your local Fibermesh representative.

COMPATIBILITY

Fibermesh 650 fibers are compatible with all concrete admixtures and performance enhancing chemicals.

SAFETY

No special handling is required with Fibermesh 650 fibers. Full Safety Data Sheets are available upon request.

PACKAGING

Fibermesh 650 macro-synthetic fibers are available in 1.5 lb (0.68 kg) toss-in degradable bags. Bags are packed into cartons, palletized and shrink-wrapped for protection during shipping. Other packaging options are available. Store materials in a cool dry place. Do not store in direct sunlight.

TECHNICAL SERVICES

Trained Fibermesh specialists are available worldwide to assist and advise in specifications and field service. Fibermesh representatives do not engage in the practice of engineering or supervision of projects and are available solely for service and support of our customers.

REFERENCE DOCUMENTS

- ACI 304 Guide for Measuring, Mixing, Transporting and Placing Concrete
- ACI 506 Guide for Shotcrete
- ASTM C1116/C1116M Standard Specification for Fiber-Reinforced Concrete and Shotcrete
- ASTM C 1399 Standard Test Method for Obtaining Average Residual-Strength of Fiber-Reinforced Concrete
- ASTM C 1436 Standard Specification for Materials for Shotcrete
- ASTM C 1550 Standard Test Method for Flexural Toughness of Fiber Reinforced Concrete (Using Centrally Loaded Round Panel)
- ASTM C 1609 /C 1609M Standard Test Method for Flexural Performance of Fiber-Reinforced Concrete (Using Beam With Third-Point Loading)
- Concrete Society (UK) Technical Report 34 Concrete Industrial Floors
- Concrete Society (UK) Technical Report 22 Non-Structural cracks in concrete
- European Standard EN 14889-2: 2006 Fibres for Concrete

SPECIFICATION CLAUSE

Fibers for concrete shall be Fibermesh 650, 100 percent virgin polyolefin fibers, e3 patented technology, containing no reprocessed olefin materials. The fibers shall conform to ASTM C1116 Type III and manufactured specifically for the reinforcement of concrete.

or

Fibers for concrete shall be Fibermesh 650, 100 percent virgin polyolefin fibers, e3 patented technology, containing no reprocessed olefin materials. The fibers shall conform to EN 14889-2: 2006 Class II and manufactured specifically for the reinforcement of concrete.

The fibers shall be manufactured in an ISO 9001:2008 certified manufacturing facility. Unless otherwise stated, Fibermesh 650 macro-synthetic fibers shall be mixed at the batch plant, at the recommended rate of ... lbs/yd³ (... kgs/m³), and mixed for sufficient time (minimum 5 minutes) to ensure uniform distribution of the fibers throughout the concrete mix. Fibrous concrete reinforcement shall be manufactured by Fibermesh, 4019 Industry Drive, Chattanooga, TN. 37416 USA, tel: 800 621 1273, web site: www.Fibermesh.com.

Fibermesh • 4019 Industry Drive • Chattanooga, TN 37416 • ORDEREXPRESS@PROPEXGLOBAL.COM
NORTH AMERICA: +1.800.621.1273 • EUROPE: +44.1246.564200 • AUSTRALIA: +61.0.2.9965.3792 • LATIN AMERICA: +1.813.285.2287

Fibermesh®, Fibercast®, Enduro®, Novomesh®, Novocon® are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.

© 2006-2017 Propex Operating Company, LLC

PCS-1158E-003 (08/2017)